



GENERAL SPECIFICATIONS

Category:	Solid
Finish:	Solid Colours
Width:	122cms
Full Roll Length:	50m
Full Roll Weight:	28 - 30 kgs
Warranty:	10 Years
Storage Temperature:	5° C to 30° C
Storage Shelf Life:	2 Years

PRODUCT CONSTRUCTION

Film Type:	PVC
Thickness	
(Average by Category):	210 µm
Adhesive:	Clear, Pressure Sensitive
Release Liner:	Bubble Free, Plottable
Pattern Direction:	Not Applicable

INSTALLATION

Installation Technique:	Dry
Installation Usage:	Interior
Installation Temperature:	12° C to 38° C
Max. Adhesive Performance:	After 3-7 Days

PRODUCT DESCRIPTION

Bodaq's range of solid colour interior films offer a versatile, easy-to-install solution for enhancing interior surfaces. With a large variety of colors, it provides a durable, low-maintenance finish ideal for updating spaces and adding a personal touch to your interior design.

DURABILITY

Bodaq Interior Films provide exceptional resilience when it comes to withstanding water, dirt, abrasion, UV radiation, and various types of wear, including issues like yellowing, cracking, scaling, and delamination.

MAINTENANCE

To maintain a perfect appearance and make your refinished surface last longer, it is recommended that you do the following:

1. Bodaq is easy to clean, so do not use harsh abrasive cleaners. If the stain is hard to remove, use ethanol mixed with water 1:1.
2. Do not use regular erasers/scrubbers on the film surface. We recommend using melamine sponges, or a microfiber towel.
3. Do not cut anything with a knife directly on the film.
4. Do not put hot metal objects on the surface wrapped with the film. If the object's temperature is higher than 50 degrees Celsius, it may damage the film.
5. In case of film peeling, please contact your installer to avoid further damage.

CERTIFICATIONS

Fire Rating (ASTM E84):	Class A (Class 1)
Incombustibility (KS F 2271:2016):	14.9 min
Flame Retardancy (DIN 4102-1):	B1 - Not Easily Flammable
Elevator Safety (TSSA, ASME A 17.1):	Compliant
Ce Wallcovering (En15102):	Compliant
REACH:	Compliant
Adhesive Strength:	10.29 N units/mm after 24h
Volatile Organic Compound Testing (En16516):	A+
Antimicrobial Activity & Efficacy:	1.0 - 1.1 log
Abrasion Resistant (ISO 9352:2012):	15.1 mg Weight Loss
Stain Resistance (Tchibo):	Excellent
Spongeability (En12956):	No Visible Change
Washability (En12956):	Extra Washable
Scratch Resistance (ASTM D3363-05):	3H Pencil Hardness
Stretch Capabilities:	Tensile Breaking Elongation (Width Direction): 18.8 N units
	Tensile Breaking Elongation (Height/ Grain Direction): 80%
	Tensile Breaking Elongation (Width Direction): 42.9 N Units/ 10 mm
	Tensile Breaking Elongation (Height/ Grain Direction): 60.2 N Units/ 10 mm
Phthalates Content:	Not Detected
Heavy Metals Content:	Not Detected
PBBs & PBDEs Content:	Not Detected

NOTE

Hyundai retains the right to modify the composition of Bodaq Interior Films at its discretion. Please be aware that the colours displayed on computer or mobile phone screens may not provide a precise representation of the actual appearance due to screen variations. To ensure an accurate understanding of the colour, we strongly recommend ordering a sample. Additionally, considering slight color variations in production batches, it is advisable to purchase the necessary quantity for your project in a single order to maintain consistent appearance during execution.

PRODUCT DISTRIBUTION

Bodaq Interior Films are available through authorized installing dealers. Samples available upon request

CONTACT INFORMATION

Bodaq Middle East
 +971 4 320 02 42
 www.bodaq.me