



GENERAL SPECIFICATIONS

| | |
|----------------------|---------------|
| Category: | Wood |
| Finish: | Painted Wood |
| Width: | 122cms |
| Full Roll Length: | 50m |
| Full Roll Weight: | 28 - 30 kgs |
| Warranty: | 10 Years |
| Storage Temperature: | 5° C to 30° C |
| Storage Shelf Life: | 2 Years |

PRODUCT CONSTRUCTION

| | |
|------------------------|---------------------------|
| Film Type: | PVC |
| Thickness | |
| (Average by Category): | 250 µm |
| Adhesive: | Clear, Pressure Sensitive |
| Release Liner: | Bubble Free, Plottable |
| Pattern Direction: | Vertical (Length) |

INSTALLATION

| | |
|----------------------------|----------------|
| Installation Technique: | Dry |
| Installation Usage: | Interior |
| Installation Temperature: | 12° C to 38° C |
| Max. Adhesive Performance: | After 3-7 Days |

NOTE

Hyundai retains the right to modify the composition of Bodaq Interior Films at its discretion. Please be aware that the colours displayed on computer or mobile phone screens may not provide a precise representation of the actual appearance due to screen variations. To ensure an accurate understanding of the colour, we strongly recommend ordering a sample. Additionally, considering slight color variations in production batches, it is advisable to purchase the necessary quantity for your project in a single order to maintain consistent appearance during execution.

PRODUCT DESCRIPTION

Bodaq's Painted Wood Collection offers a vibrant alternative to traditional wood finishes. Available in a wide range of colours, they adds a bold and contemporary twist to interior design. This collection offers the charm of wood with a colourful twist, making it an excellent choice for those seeking a lively and creative atmosphere in their space.

DURABILITY

Bodaq Interior Films provide exceptional resilience when it comes to withstanding water, dirt, abrasion, UV radiation, and various types of wear, including issues like yellowing, cracking, scaling, and delamination.

MAINTENANCE

To maintain a perfect appearance and make your refinished surface last longer, it is recommended that you do the following:

1. Bodaq is easy to clean, so do not use harsh abrasive cleaners. If the stain is hard to remove, use ethanol mixed with water 1:1.
2. Do not use regular erasers/scrubbers on the film surface. We recommend using melamine sponges, or a microfiber towel.
3. Do not cut anything with a knife directly on the film.
4. Do not put hot metal objects on the surface wrapped with the film. If the object's temperature is higher than 50 degrees Celsius, it may damage the film.
5. In case of film peeling, please contact your installer to avoid further damage.

CERTIFICATIONS

| | |
|--|--|
| Fire Rating (ASTM E84): | Class A (Class 1) |
| Incombustibility (KS F 2271:2016): | 14.9 min |
| Flame Retardancy (DIN 4102-1): | B1 - Not Easily Flammable |
| Elevator Safety (TSSA, ASME A 17.1): | Compliant |
| Ce Wallcovering (En15102): | Compliant |
| REACH: | Compliant |
| Adhesive Strength: | 10.29 N units/mm after 24h |
| Volatile Organic Compound Testing (En16516): | A+ |
| Antimicrobial Activity & Efficacy: | 1.0 - 1.1 log |
| Abrasion Resistant (ISO 9352:2012): | 15.1 mg Weight Loss |
| Stain Resistance (Tchibo): | Excellent |
| Spongeability (En12956): | No Visible Change |
| Washability (En12956): | Extra Washable |
| Scratch Resistance (ASTM D3363-05): | 3H Pencil Hardness |
| Stretch Capabilities: | Tensile Breaking Elongation (Width Direction): 18.8 N units |
| | Tensile Breaking Elongation (Height/ Grain Direction): 80% |
| | Tensile Breaking Elongation (Width Direction): 42.9 N Units/ 10 mm |
| | Tensile Breaking Elongation (Height/ Grain Direction): 60.2 N Units/ 10 mm |
| Phthalates Content: | Not Detected |
| Heavy Metals Content: | Not Detected |
| PBBs & PBDEs Content: | Not Detected |

PRODUCT DISTRIBUTION

Bodaq Interior Films are available through authorized installing dealers. Samples available upon request

CONTACT INFORMATION

Bodaq Middle East
+971 4 320 02 42
www.bodaq.me